

TIMBER : LOCAL PINE



GENERAL DESCRIPTION

Grain is usually straight. Knots are common and growth rings are prominent.

Texture: Fine but uneven.

Usually easy to work away from knots.

TIMBER DESCRIPTION

Density approximately 550kg/m³ at 12% moisture content

UTILISATION

Timber used locally for house construction.

TIMBER : MALAGASSY PINE



GENERAL DESCRIPTION

Grain is usually straight. Knots are common and growth rings are prominent.

Texture: Fine but uneven.

Usually easy to work away from knots.

TIMBER DESCRIPTION

Density approximately 550kg/m³ at 12% moisture content

UTILISATION

Timber used locally for house construction.

TIMBER : SHUTTER BOARDS



GENERAL DESCRIPTION

The quality of products comply with various standard like GB/T9846-2004 and EN314-1:2004.

TIMBER DESCRIPTION

Density approximately 586kg/m³ at 8% moisture content.

WBP Phenolic glue, full hardwood core, 18mm x 1220mm x 2440mm 130g/m²

UTILISATION

Concrete formwork where smooth struck finish is required; also high re-usage factor